LAM0795 PVC Laminate Film

Description

Soft Monomeric PVC film Color: Transparent. Surface: Glossy or matt

Release paper

 95 ± 10 gsm PE-Coated silicon paper.

Adhesive

Solvent polyacrylate, Permanent, Transparent Color.

Technical datas

1echinear datas	
Thickness (without protective paper and adhesive)	70 micron Monomeric PVC film
Dimensional stability (FINAT TM14)	Adhered to steel, No shrinkage in cross direction, in length 0.50mm max
Temperature resistance	Adhered to aluminum20°C to +65°C, no variation.
Adhesive	Solvent polyacrylate Permanent Transparent adhesive
Seawater resistance (DIN 50021)	Adhered to aluminum, after 48h/23°C no variation.
Adhesive power (FINAT TM 1, initial, stainless steel)	8~10 N/25 mm
Adhesive power (FINAT TM 1,untimate, stainless steel)	11-14 N/25 mm
Shelf life	1 year stroed at 22° C/50-55 % RH
Application temperature	min. +10°C
Standard length	50M / 100M / 200M
Width	2.02m/1.82m/1.52m/1.37m/1.27m/1.07m/1.06m/0.914m

Attention:

After printing the ink must be thoroughly dry in order to avoid any affect on the later combination with the laminate. Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material.

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications customers should independently determine the suitability of this material for their specific purpose, prior to use.